

LIGHT GREEN SPORT COATING

100% acrylic base coating for tennis, basketball, pickleball, & multi-purpose courts

- Exceptional Durability and fade resistance
- Safe non-slip surface
- Water-Based
- Vibrant Finish

MANUFACTURER

JETCOAT
472 Brehl Avenue
Columbus, Ohio 43223
Phone: 800-394-0047
www.JETCOATinc.com

DESCRIPTION

Surface 1 Light Green Sport Coating is a 100% acrylic coating for tennis, basketball, pickleball, and multi-purpose courts and recreational areas. Surface 1 Light Green Sport Coating is fortified with sand to provide a safe, non-slip surface. Our revolutionary formula provides superior hiding and durability with two coats.

USES

Sport surfaces, recreational surfaces, & more.

SURFACE PREPARATION

New asphalt must cure for a minimum of 14 days, and new concrete must cure for a minimum of 30 days before application. Courts should be sloped 1% in one direction to prevent standing water on the surface.

For concrete surfaces, ensure:

- Court is built with 2 layers of 6 mil vapor barrier under the slab and perimeter drainage to prevent blistering and peeling of coatings
- Surface has a medium-broom finish or shot blast to similarly roughened surface texture

- No curing compounds on the surface (moisture curing only)
- Acid etch surface after full cure and before application of coatings for chemical bond of coatings
- Prime concrete prior to application with Surface 1 Patch Binder (1 part Patch Binder to 1 part water) on new/uncoated concrete surfaces

Clean Surface - Sweep all dirt and loose debris from surface. Remove dirt and vegetation from cracks with screwdriver, wire brush or another suitable tool. Scrub all oil & residue stains with household detergent and water. Rinse off entire surface with water and allow to dry thoroughly before applying Surface 1 repair products & coatings.

Fill cracks and level low areas - Fill cracks up to 1" wide with Surface 1 Acrylic Crack Filler or Patch Binder mix. Level any puddled areas over 1/16" (commonly measured with a US nickel) with Patch Binder mix.

Allow crack filler to dry prior to applying Surface 1 Court Resurfacer or Sport Coating Base (dry time varies depending on width and depth of crack).

After surface cleaning and repairs, apply 1 or more coats of Surface 1 Court Resurfacer to fill voids in pavement and conceal repairs.

MIXING

Surface 1 Light Green Sport Coating is a pre-tinted product with sand factory mixed. The product needs water mixed in before application. Stir thoroughly before applying. For court surfaces in good condition without loss of texture or in need of crack repairs, one coat of Light Green Sport Coating can be applied.

The following mix design is for a 55-gallon drum of Surface 1 Light Green Sport Coating:

Surface 1 Light Green Sport Coating.....55 gallons
Water.....20-25 gallons

Mix the material to a smooth, uniform consistency

APPLICATION

Apply Surface 1 Light Green Sport Coating with a soft rubber squeegee (50-60 durometer recommended for squeegee rubber softness). Surface One recommends applying the complete multi-coat system to fill surface voids, change color schemes, and achieve a longer-lasting surface. Allow each coat to dry completely before applying additional coats or lines.

WEATHER CONDITIONS

Application temperature must be a minimum of 50 °F and rising. Do not apply when temperature is expected to drop below 50 °F within a 24- hour period. In areas where dew or fog accumulates in the early evening, it is best to coat in the morning. Stop coating by early afternoon (3:00 pm) to prevent wash off, which will occur if dew, fog, or rain arrives before coating dries. Do not apply if rain is imminent or forecast within 24 hours of application.

COVERAGE (APPROXIMATE)

1 gallon will cover approximately 100 -125 sq. ft., depending on pavement porosity (6,875 sq. ft. per 55-gallon drum).

PRECAUTIONS

Do Not Freeze. Do Not Store at Temperatures Below 50 °F.

CAUTION

KEEP OUT OF REACH OF CHILDREN. Protect from freezing. Do not take internally. If swallowed, call a physician immediately. In case of contact with eyes, flush immediately with water for 15 minutes and call a physician. Store material with container tightly closed and upright to avoid spillage. Do not store material in direct sunlight or in areas exceeding 100 degrees Fahrenheit. In case of spill, absorb and dispose of in accordance with Federal, State, and local regulations.

LIMITED WARRANTY

JETCOAT warrants this product to be of merchantable quality when used or applied in accordance with the instructions hereon. JETCOAT does not warrant this product to be suitable for any particular use or purpose other than for which it is intended. Liability is limited to replacement of the product, or at its option, to a refund of the price thereof. There are no other warranties, either expressed or implied. Liability for any incidental or consequential damage or loss is specifically excluded at all times.